



**CHEMFAB® CF110** is a Primary Series PTFE-coated glasscloth. It has an extra smooth and glossy surface and provides excellent release and chemical resistant properties.

It is typically used in release sheet applications.

Standard Widths:	mm	1000, 1525	_
Temperature Resistance:	°C	-150 to +260	-
PTFE Content:	%	62	-
Trap Tear Strength:	N	65 x 40	FTMS 191A-5136
Tensile Strength:	N/cm	540 x 390	FTMS 191A-5102
Thickness:	mm	0.250	FTMS 191A-5030
Weight:	g/m²	545	FTMS 191A-504
TYPICAL PROPERTIES	UNIT	VALUE	TEST METHOD

<sup>\*</sup>Formerly CF 700-10 G

Saint-Gobain Performance Plastics sales, fabrication and distribution facilities are situated at the following locations:

Ireland

Tel. +353 65 9080170 Fax. +353 65 9080177

E-mail: aff.europe@saint-gobain.com

Germany

Tel. +49 221 9714080 Fax. +49 221 97140835

E-mail: aff.germany@saint-gobain.com

France

Tel. +33 4 68635353 Fax. +33 4 68632646

E-mail: aff.france@saint-gobain.com

UK

Tel. +44 1706 746900 Fax. +44 1706 746991

E-mail: aff.uk@saint-gobain.com

Spain

Tel. +34 902 300 229 Fax. +34 902 294 429

E-mail: aff.spain@saint-gobain.com

www.fff.saint-gobain.com

CHEMFAB® is a registered trademark.

The data listed herein fall within the normal range of product properties for the products described, but they should not be used to establish specification limits nor used alone as the basis of design. SAINT-GOBAIN assumes no obligation or liability for any advice furnished by it or for results obtained to these products. All such advice is provided graits and Buyer assumes sole responsibility for results obtained in reliance thereon. SAINT-GOBAIN warrants that the material Itself does not knowingly infringe any patent, but no license is implied nor is any further warranty made.

©2008 Saint-Gobain Performance Plastics Corporation KIIR-0108-028