

NYLATRON® NSM (Polyamide - PA 6 + solid lubricant)

NYLATRON NSM is a proprietary cast nylon 6 formulation containing solid lubricant additives which grant this material self lubricity, excellent frictional behaviour, superior wear resistance and outstanding pressure-velocity capabilities (up to 5 times higher than conventional cast nylons). Being particularly suited for higher velocity, unlubricated moving parts applications, it is the perfect complement to the oil-filled grade ERTALON LFX.



Physical properties (indicative values [■])

PROPERTIES	Test methods	Units	VALUES
Colour	-	-	grey
Density	ISO 1183-1	g/cm ³	1.14
Water absorption:			
- after 24/96 h immersion in water of 23 °C (1)	ISO 62	mg	40/76
	ISO 62	%	0.59/1.12
- at saturation in air of 23°C / 50 % RH	-	%	2
- at saturation in water of 23 °C	-	%	6.3
Thermal Properties (2)			
Melting temperature (DSC, 10 °C/min)	ISO 11357-1/-3	°C	215
Glass transition temperature (DSC, 20 °C/min) - (3)	ISO 11357-1/-2	°C	-
Thermal conductivity at 23 °C	-	W/(K.m)	0.29
Coefficient of linear thermal expansion:			
- average value between 23 and 60 °C	-	m/(m.K)	80 x 10 ⁻⁶
- average value between 23 and 100 °C	-	m/(m.K)	95 x 10 ⁻⁶
Temperature of deflection under load:			
- method A: 1.8 MPa	+ ISO 75-1/-2	°C	75
Max. allowable service temperature in air:			
- for short periods (4)	-	°C	165
- continuously : for 5,000 / 20,000 h (5)	-	°C	105/90
Min. service temperature (6)	-	°C	-30
Flammability (7):			
- "Oxygen Index"	ISO 4589-1/-2	%	-
- according to UL 94 (3 / 6 mm thickness)	-	-	HB / HB
Mechanical Properties at 23 °C (8)			
Tension test (9):			
- tensile stress at yield / tensile stress at break (10)	+ ISO 527-1/-2	MPa	78 / -
	++ ISO 527-1/-2	MPa	50 / -
- tensile strength (10)	+ ISO 527-1/-2	MPa	80
- tensile strain at yield (10)	+ ISO 527-1/-2	%	5
- tensile strain at break (10)	+ ISO 527-1/-2	%	25
	++ ISO 527-1/-2	%	> 50
- tensile modulus of elasticity (11)	+ ISO 527-1/-2	MPa	3150
	++ ISO 527-1/-2	MPa	1525
Compression test (12):			
- compressive stress at 1 / 2 / 5 % nominal strain (11)	+ ISO 604	MPa	23 / 44 / 81
Creep test in tension (9):			
- stress to produce 1 % strain in 1000 h ($\sigma_{1/1000}$)	+ ISO 899-1	MPa	18
	++ ISO 899-1	MPa	8
Charpy impact strength - Unnotched (13)	+ ISO 179-1/1eU	kJ/m ²	100
Charpy impact strength - Notched	+ ISO 179-1/1eA	kJ/m ²	4
Izod impact strength - Notched	+ ISO 180/A	kJ/m ²	4
	++ ISO 180/A	kJ/m ²	7
Ball indentation hardness (14)	+ ISO 2039-1	N/mm ²	150
Rockwell hardness (14)	+ ISO 2039-2	-	M 81
Electrical Properties at 23 °C			
Electric strength (15)	+ IEC 60243-1	kV/mm	25
	++ IEC 60243-1	kV/mm	17
Volume resistivity	+ IEC 60093	Ohm.cm	> 10 ¹⁴
	++ IEC 60093	Ohm.cm	> 10 ¹²
Surface resistivity	+ IEC 60093	Ohm	> 10 ¹³
	++ IEC 60093	Ohm	> 10 ¹²
Relative permittivity ϵ_r : - at 100 Hz	+ IEC 60250	-	3.6
	++ IEC 60250	-	6.6
- at 1 MHz	+ IEC 60250	-	3.2
	++ IEC 60250	-	3.7
Dielectric dissipation factor tan δ : - at 100 Hz	+ IEC 60250	-	0.012
	++ IEC 60250	-	0.14
- at 1 MHz	+ IEC 60250	-	0.016
	++ IEC 60250	-	0.05
Comparative tracking index (CTI)	+ IEC 60112	-	600
	++ IEC 60112	-	600

Note: 1 g/cm³ = 1,000 kg/m³; 1 MPa = 1 N/mm²; 1 kV/mm = 1 MV/m.

AVAILABILITY

Round Rods: Ø 50-500 mm - **Plates:** Thicknesses 10-100 mm - **Tubes:** O.D. 50-600 mm

NYLATRON® is a registered trademark of the **Quadrant Group**.

All information supplied by or on behalf of Quadrant Engineering Plastic Products in relation to its products, in any form, is supported by research and believed to be reliable, but Quadrant Engineering Plastic Products assumes no liability whatsoever in respect of application, processing or use made of the aforementioned information or products, or any consequence thereof. The buyer undertakes all liability in respect of the application, processing or use of the aforementioned information or product, whose quality and other properties he shall verify, or any consequence thereof. No liability whatsoever shall attach to Quadrant Engineering Plastic Products for any infringement of the rights owned or controlled by a third party in intellectual, industrial or other

Legend:

+ : values referring to dry material
++ : values referring to material in equilibrium with the standard atmosphere 23 °C / 50 % RH (mostly derived from literature)

- According to method 1 of ISO 62 and done on discs Ø 50 x 3 mm.
- The figures given for these properties are for the most part derived from raw material supplier data and other publications.
- Values for this property are only given here for amorphous materials and not for semi-crystalline ones.
- Only for short time exposure (a few hours) in applications where no or only a very low load is applied to the material.
- Temperature resistance over a period of 5,000/20,000 hours. After these periods of time, there is a decrease in tensile strength – measured at 23 °C – of about 50 % as compared with the original value. The temperature values given here are thus based on the thermal-oxidative degradation which takes place and causes a reduction in properties. Note, however, that the maximum allowable service temperature depends in many cases essentially on the duration and the magnitude of the mechanical stresses to which the material is subjected.
- Impact strength decreasing with decreasing temperature, the minimum allowable service temperature is practically mainly determined by the extent to which the material is subjected to impact. The value given here is based on unfavourable impact conditions and may consequently not be considered as being the absolute practical limit.
- These estimated ratings, derived from raw material supplier data and other publications, are not intended to reflect hazards presented by the material under actual fire conditions. There is no 'UL File Number' available for the NYLATRON NSM stock shapes.
- The figures given for the properties of dry material (+) are for the most part average values of tests run on test specimens machined out of rods Ø 50 mm. Except for the hardness tests, the test specimens were then taken from an area mid between centre and outside diameter, with their length in longitudinal direction of the rod.
- Test specimens: Type 1 B
- Test speed: 50 mm/min [chosen acc. to ISO 10350-1 as a function of the ductile behaviour of the material (tough or brittle)].
- Test speed: 1 mm/min
- Test specimens: cylinders Ø 12 x 30 mm
- Pendulum used: 15 J
- Measured on 10 mm thick test specimens (discs), mid between center and outside diameter.
- Electrode configuration: Ø 25 / Ø 75 mm coaxial cylinders ; in transformer oil according to IEC 60296 ; 1 mm thick test specimens.

■ This table is a valuable help in the choice of a material. The data listed here fall within the normal range of product properties. **However, they are not guaranteed and they should not be used to establish material specification limits nor used alone as the basis of design.**