

**CHEMSTIK® SPSA S** Range is comprised of high quality skived PTFE coated with silicone pressure sensitive adhesive. It provides the unique characteristics of PTFE in a form suitable for application as a surface liner to wood, metal or plastic. A separate liner is applied to the adhesive surface for ease of application.

**CHEMSTIK® SPSA S** liners exhibit excellent release properties and are unaffected by most chemicals and solvents.

TYPICAL PROPERTIES	SPSA-3 S	SPSA-5 S	SPSA-10 S	SPSA-20 S	TEST METHOD
<b>Weight</b> (g/m <sup>2</sup> )	170	280	540	1080	FTMS 191A-5041
<b>Thickness</b> (mm)	0.080	0.130	0.250	0.500	FTMS 191A-5030
<b>Adhesive Thickness</b> (mm)	0.045	0.045	0.045	0.045	FTMS 191A-5030
<b>Tensile Strength</b> (N/cm)	35	53	96	184	FTMS 191A - 5102
<b>Minimum Elongation</b> (%)	200	200	200	200	FTMS 191A-5102
<b>Peel Adhesion</b> (N/cm)	5.4	5.6	5.9	6.8	ASTM D3330-83
<b>Polyken Tack</b> (g)	600	550	420	550	-
<b>Standard Widths</b> (mm)	990	1000	1000	1000	-

Saint-Gobain Performance Plastics sales, fabrication and distribution facilities are situated at the following locations:

#### Ireland

Tel. +353 65 9080170  
Fax. +353 65 9080177  
E-mail: [aff.europe@saint-gobain.com](mailto:aff.europe@saint-gobain.com)

#### Germany

Tel. +49 221 9714080  
Fax. +49 221 97140835  
E-mail: [aff.germany@saint-gobain.com](mailto:aff.germany@saint-gobain.com)

#### France

Tel. +33 4 68635353  
Fax. +33 4 68632646  
E-mail: [aff.france@saint-gobain.com](mailto:aff.france@saint-gobain.com)

#### UK

Tel. +44 1706 746900  
Fax. +44 1706 746991  
E-mail: [aff.uk@saint-gobain.com](mailto:aff.uk@saint-gobain.com)

#### Spain

Tel. +34 902 300 229  
Fax. +34 902 294 429  
E-mail: [aff.spain@saint-gobain.com](mailto:aff.spain@saint-gobain.com)

**[www.fff.saint-gobain.com](http://www.fff.saint-gobain.com)**

CHEMFAB® is a registered trademark.

The data listed herein fall within the normal range of product properties for the products described, but they should not be used to establish specification limits nor used alone as the basis of design. SAINT-GOBAIN assumes no obligation or liability for any advice furnished by it or for results obtained to these products. All such advice is provided gratis and Buyer assumes sole responsibility for results obtained in reliance thereon. SAINT-GOBAIN warrants that the material itself does not knowingly infringe any patent, but no license is implied nor is any further warranty made.

©2008 Saint-Gobain Performance Plastics Corporation  
KIIR-0208-057